KAKE AIRPORT



2004 Alaska Airport Pavement Condition Report

Scott Gartin, P.E.
State Pavement Engineer
Statewide Materials Section, Alaska DOT&PF
5800 E. Tudor Road
Phone: (907) 269-6244 Fax: (907) 269-6231
Email: scott_gartin@dot.state.ak.us

Maps and report compiled by
H. June Finkbiner
Central Region Materials, Alaska DOT&PF

KAKE AIRPORT - 2004

Contents:

- A Pavement Strength Form showing project history, latest Pavement Condition Index (PCI) data, pavement strength ratings (if available) and other useful information
- A Pavement Condition Survey – PCI Sample Unit Layout Plan
- PCI maps showing as-measured and predicted pavement conditions
- Age map showing pavement age as of 2004
- A Branch PCI Condition Report
- A Section PCI Condition Report

Airport Information:

- Location: Kake Airport is located about 1 mile east of the town of Kake that is near the north shore of Kuiu Island in the central part of Southeast Alaska. Kake is a fishing and logging town.
- District: Southeast
- Airport Manager: Delbert Kadake
- District Maintenance Manager: Gary Franzen, Contract Manager
- Pavement Surface: There are approximately 530,000 square feet of 1991 asphalt concrete pavement on the airport, not counting the access road.
- Last Pavement Construction: 1991
- Pavement layout:
  The airport consists of Runway 10-28 (4000' x 100') that has a displaced threshold on the east end and an Apron with a short Taxiway "A". The runway was divided into two Sections with the eastern 1000' beyond the displaced threshold being Section 2. This airport serves General Aviation propeller driven aircraft. It is unfenced and without controlled access.
- Design Aircraft: General Aviation
- 2003 Enplanements: 2,902 – up 38% from 2002
- Airport Class: Non-Primary
- Last pavement condition survey: May 14, 2003
- Next planned pavement condition survey: 2006
- 2004 reported pavement maintenance and/or changed conditions: Two settlement areas in on the south end of the runway, Section 6100-02, are progressing and creating problems.

Recommendations: Seal cracks wider than ¼", patch and repair as needed. Apply emulsified seal coat to grader scrapes and any areas with exposed aggregates. Consider Geotechnical Investigation of the settlement areas in Section 6100-02 to determine the best way to repair it.

Date: 7 /24/2003

Branch Condition Report

Pavement Database: NetworkID: Kake

Branch ID	Number of Sections	Sum Section Length (Ft)	Avg Section Width (Ft)	True Area (SqFt)	Use	Average PCI	PCI Standard Deviation	Weighted Average PCI
100 (Taxiway A)	1	212.00	35.00	9572.00	TAXIWAY	71.00	0.00	71.00
4100 (Apron)	1	600.00	200.00	120000.00	APRON	90.00	0.00	90.00
6100 (Runway 10-28)	2	4000.00	100.00	400000.01	RUNWAY	81.50	2.50	80.25

Branch Condition Report

Pavement Database:

Use Category	Number of Sections	Total Area (SqFt)	Arithmetic Average PCI	Average PCI STD.	Weighted Average PCI
APRON	1	120000.00	90.00	0.00	90.00
RUNWAY	2	400000.01	81.50	2.50	80.25
TAXIWAY	1	9572.00	71.00	0.00	71.00
All	4	529572.01	81.00	6.96	82.29

Date: 7 /24/2003

Section Condition Report

Pavement Database: *NetworkID: Kake*

Branch ID	Section ID	Last Const. Date	Surface	Use	Rank	Lanes	True Area (SqFt)	Last Inspection Date	Age At Inspection	PCI
100 (Taxiway A)	100-01	08/01/1991	AC	TAXIWAY	P	0	9572.00	05/14/2003	12	71.00
4100 (Apron)	4100-01	08/01/1991	AC	APRON	P	0	120000.00	05/14/2003	12	90.00
6100 (Runway 10-28)	6100-01	08/01/1991	AC	RUNWAY	P	0	300000.01	05/14/2003	12	79.00
6100 (Runway 10-28)	6100-02	08/01/1991	AC	RUNWAY	P	0	100000.00	05/14/2003	12	84.00

Pavement Database:

Age Category	Average Age At Inspection	Total Area (SqFt)	Number of Sections	Arithmetic Average PCI	PCI Standard Deviation	Weighted Average PCI
11-15	**12.00**	**529572.01**	**4**	**81.00**	**6.96**	**82.29**
All	**12.00**	**529572.01**	**4**	**81.00**	**6.96**	**82.29**

PAVEMENT STRENGTH SURVEY

STATE Alaska | **CITY** Kake | **AIRPORT** Kake | This is a variation of FAA Form 5320-1-1

IDENT.	NAME	CONSTRUCTION DATES ORIG.	CONSTRUCTION DATES OVERLAY	CONSTRUCTION AGENCY	SOURCE OF INFORMATION	Existing Pavement Conditions (PCI) at last inspection	Soil Class	Subbase Course	Base Course	Surface Course	Overlay	Pavement Strength
						RUNWAYS						
6100-01	Runway 10-28 Section 1	1991			S.E. Region	79				2" AC		General Aviation
6100-02	Runway 10-28 Section 2	1991			SE Region	84				AC		General Aviation
						TAXIWAYS						
100-01	Taxiway A	1991			S.E. Region	71				AC		
						APRONS						
4100-01	General Aviation Apron	1991			S.E. Region	90				AC		

REMARKS:
This Airport serves small General Aviation Aircraft

Date of Site Inspection:	5/14/2003	Evaluated By:	S. Gartin	11/29/2004

Pavement Condition Survey - PCI Sample Unit Layout Plan

State	City	Airport	Airport AFE Code:	Site No.
Alaska	Kake	Kake		50393.01*A



LEGEND

[ ] Branch/Section Identifier

Sample Unit

Unit of Pavement Sampled 2003

Map compiled December 10, 2004

Kake Airport

Pavement Surface Age
2004

Airport Code: AFE
Site Number: 50393.01*A

[ ] Branch-Section Identifier



- 0 - 4 yrs
- 5 - 9 yrs
- 10 - 14 yrs
- 15 - 19 yrs
- 20 - 24 yrs
- 25 - 29 yrs
- >30 yrs

Map Compiled July 2003 (Revised April 2005)
by Central Region Materials, AK DOT&PF

Kake Airport

Pavement Condition Index (PCI)
Measured Values for the Year 2003

Airport Code: AFE
Site Number: 50393.01*A

[ ] Branch-Section Identifier



Minimum PCI for Runway = 70
Minimum PCI for Taxiways and Aprons = 60

PCI Values	General Pavement Recommendations
85 - 100	Do Nothing or Preventative Maintenance
70 - 84	Preventative Maintenance
60 - 69	Corrective Maintenance
55 - 59	Rehabilitate
40 - 54	Rehabilitate
25 - 39	Reconstruct
10 - 24	Reconstruct
0 - 9	Reconstruct

Map Compiled July 2003 (Revised April 2005)
by Central Region Materials, AK DOT&PF

Kake Airport

Pavement Condition Index (PCI)
Predicted Values for the Year 2004

Airport Code: AFE
Site Number: 50393.01*A

[ ] Branch-Section Identifier



Minimum PCI for Runway = 70
Minimum PCI for Taxiways and Aprons = 60

PCI Values	General Pavement Recommendations
85 - 100	Do Nothing or Preventative Maintenance
70 - 84	Preventative Maintenance
60 - 69	Corrective Maintenance
55 - 59	Rehabilitate
40 - 54	Rehabilitate
25 - 39	Reconstruct
10 - 24	Reconstruct
0 - 9	Reconstruct

Map Compiled July 2003 (Revised April 2005)
by Central Region Materials, AK DOT&PF

Kake Airport

Pavement Condition Index (PCI)
Predicted Values for the Year 2005

Airport Code: AFE
Site Number: 50393.01*A

[ ] Branch-Section Identifier



PCI Values	General Pavement Recommendations
85 - 100	Do Nothing or Preventative Maintenance
70 - 84	Preventative Maintenance
60 - 69	Corrective Maintenance
55 - 59	Rehabilitate
40 - 54	Rehabilitate
25 - 39	Reconstruct
10 - 24	Reconstruct
0 - 9	Reconstruct

Map Compiled July 2003 (Revised April 2005)
by Central Region Materials, AK DOT&PF

Kake Airport

Pavement Condition Index (PCI)
Predicted Values for the Year 2006

Airport Code: AFE
Site Number: 50393.01*A

[ ] Branch-Section Identifier



PCI Values	General Pavement Recommendations
85 - 100	Do Nothing or Preventative Maintenance
70 - 84	Preventative Maintenance
60 - 69	Corrective Maintenance
55 - 59	Rehabilitate
40 - 54	Rehabilitate
25 - 39	Reconstruct
10 - 24	Reconstruct
0 - 9	Reconstruct

Map Compiled July 2003 (Revised April 2005)
by Central Region Materials, AK DOT&PF

Kake Airport

Pavement Condition Index (PCI)
Predicted Values for the Year 2007

Airport Code: AFE
Site Number: 50393.01*A

[ ] Branch-Section Identifier



Minimum PCI for Runway = 70
Minimum PCI for Taxiways and Aprons = 60

PCI Values	General Pavement Recommendations
85 - 100	Do Nothing or Preventative Maintenance
70 - 84	Preventative Maintenance
60 - 69	Corrective Maintenance
55 - 59	Rehabilitate
40 - 54	Rehabilitate
25 - 39	Reconstruct
10 - 24	Reconstruct
0 - 9	Reconstruct

Map Compiled July 2003 (Revised April 2005)
by Central Region Materials, AK DOT&PF

Kake Airport

Pavement Condition Index (PCI)
Predicted Values for the Year 2008

Airport Code: AFE
Site Number: 50393.01*A

[ ] Branch-Section Identifier



PCI Values	General Pavement Recommendations
85 - 100	Do Nothing or Preventative Maintenance
70 - 84	Preventative Maintenance
60 - 69	Corrective Maintenance
55 - 59	Rehabilitate
40 - 54	Rehabilitate
25 - 39	Reconstruct
10 - 24	Reconstruct
0 - 9	Reconstruct

Map Compiled July 2003 (Revised April 2005)
by Central Region Materials, AK DOT&PF